



Spectral	SATAjet 5000 B RP	SATAjet 5000 B HVLP	SATAjet 4000 B RP	SATAjet 4000 B HVLP	SATAjet 3000 B RP	SATAjet 3000 B HVLP
UNDER 345 Wash primer	1.2 / 1.3 / 1.4	1.2 / 1.3 / 1.4	1.2 / 1.3 / 1.4	1.2 / 1.3 / 1.4	1.2 / 1.3 / 1.4	1.2 / 1.3 / 1.4
	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar
UNDER 385 Epoxy nonsanding primer	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3
	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar
UNDER 315 / 325 / 325-00 / 335 / 365 Acrylic nonsanding primer	1.2 / 1.3 / 1.4	1.2 / 1.3	1.2 / 1.3 / 1.4	1.2 / 1.3	1.2 / 1.3 / 1.4	1.2 / 1.3
	1.5 - 2.0 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar
SPECTRAL 2K	1.2 / 1.3 / 1.4	1.3 / 1.4	1.2 / 1.3 / 1.4	1.3 / 1.4	1.2 / 1.3 / 1.4	1.3 / 1.4
	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar	1.8 - 2.2 bar	2.0 bar
SPECTRAL BASE 2.0 Solventborne basecoat	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3
	1.6 - 2.0 bar	1.6 - 2.0 bar	1.6 - 2.0 bar	1.6 - 2.0 bar	1.6 - 2.0 bar	1.6 - 2.0 bar
SPECTRAL WAVE 2.0 Waterborne basecoat	1.2 / 1.3	1.2 / WSB / 1.3	1.2 / 1.3	1.2 / WSB / 1.3	1.2 / 1.3	1.2 / WSB / 1.3
	2.0 bar	1.6 - 2.0 bar	2.0 bar	1.6 - 2.0 bar	2.0 bar	1.6 - 2.0 bar
KLAR 505 / 565 Acrylic clearcoat	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3	1.2 / 1.3
	1.5 - 2.0 bar	2.0 bar	2.0 - 2.2 bar	2.0 bar	2.0 - 2.5 bar	2.0 bar
KLAR 535 / 545 / 555 / 575 Acrylic clearcoat	1.2 / 1.3 / 1.4	1.3 / 1.4	1.2 / 1.3 / 1.4	1.3 / 1.4	1.2 / 1.3 / 1.4	1.3 / 1.4
	1.5 - 2.0 bar	2.0 bar	2.0 - 2.2 bar	2.0 bar	2.0 - 2.5 bar	2.0 bar

<sup>1)</sup>Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

\*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.



Spectral	SATAjet 100 B F RP	SATAjet 100 B F HVLP
UNDER 345 Wash primer	--	1.4
	--	2.0 bar
UNDER 325-00 / 335 / 355 / 365 Acrylic filler	1.6 / 1.8 / 2.0	1.7 / 1.9
	2.0 bar	2.0 bar

<sup>1)</sup>Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

\*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. |  
 Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.